











ARTISTIC STONE GLASS TECHNICAL DATA

TEST		RESULT
	Water Absorption	0.01 %
	Dimension Deflection Length & Width Thickness Warpage Angle Straightness Flatness	SIZE \geq 300, $\pm 0.20\%$ SIZE \leq 300, $\pm 0.30\%$ ± 0.20 $\pm 0.15\%$ $\pm 0.15\%$ $\pm 0.20\%$ $\pm 0.20\%$
	Bending Strength (N/mm ²)	≥ 50
	Abrasion Resistance	≥ 3 GRADE
	Thermal Expansion Coefficient(M°C ⁻¹)	≤ 9.2
	Thermal Shock Resistance No cracks after 10 times test	No visible Alterations
	Surface Hardness(MOHS)	≥ 6
	Slip Resistance DIN 51097 DIN 51130 ESN 744507	B R9 0,3 - 0,73
	Frost Resistance No cracks after Frost test	No Breaks or Visible effect
	Stain Resistance (Stains Removed With Warm Running Water)	≥ 6 GRADE
	Color Resistance to Light	No visible color change

