















CONCRETA PRODUCT SPECIFICATION

GLAZED FLOOR TILE 60x60cm

Pressed Ceramic Tiles International Norms ISO 13006-10545/98

GROUP: B1b

No.	Icon	Test item	Unit	Requirements of Standard		Test result	Result
1		Dimensional variation	(%)	length of side	0.6	< 0.6	Qualified
2		Side straightness	(%)	± 0.5		< 0.5	Qualified
3		Squareness	(%)	± 0.6		< 0.5	Qualified
4		Surface flatness	(%)	Center curvature degree	± 0.5	< 0.5	Qualified
				Warping degree	± 0.5	< 0.5	Qualified
				Side curvature degree	± 0.5	< 0.5	Qualified
5		Surface quality	—	Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile		conformed	Qualified
6		Water absorption	(%)	Average value ≤ 3 individual ≤ 3.3		< 3 < 3.0	Qualified
7		Breaking strength	N	When thickness ≥ 7.5mm the Average value ≥ 700		< 700	Qualified
8		Rupture modulus	Mpa	Average value ≥ 30 individual ≥ 27		> 30 > 27	Qualified
9		Abrasion resistance	revs	1700		>1700	Qualified Class 4
10		Scratch resistance	MOH	—		6	Qualified
11		Frost resistance	—	No cracking after test		conformed	Qualified
12		Resistance to acids & alkalis	—	not less than grade GB		Grade GA	Qualified
13		Chemical resistance	—	not less than grade GB		Grade GA	Qualified
14		Slip resistance	R DCoF	Ramp slip rating test DCoF: 0.42		R11 > 0.42	Qualified

CONCRETA



Italian ink-jet design floor tiles



maniscalco®
australian for mosaics®

KREM

CONCRETA



Bianco



Grigio



Cenere

Available Finishes: Matte / Exterior

Packaging: *24 x 24"	4 pcs. / ctn.	15.5 sqft / ctn.	66.14 lbs. / ctn.	3' 6" pallet: 40ctn. / pallet	620 sqft / pallet
	8 pcs. / ctn.	15.5 sqft / ctn.	66.14 lbs. / ctn.	3' 6" pallet: 40ctn. / pallet	620 sqft / pallet

*Sizes are nominal



maniscalco
australian for mosaics